

Weight		14.5 oz/sy \pm 10%
Thickness		0.017" \pm 0.001"
Tensile Strength (W x F).....	FED STD 191/5102	275x175 lb/in avg.
Tear Strength (W x F).....	FED STD 191/5136	40x20 lb min avg.
Burst Strength	ASTM-D-774	600 psi min.
Permeability	ASTM-E-96-66A	0.05 perms
Corrosion Resistance	HH-B-100B.....	Passes
Temperature Resistance		250° F max.
Flame Resistance	FED STD 191/5903.2	
Flame Out.....		1 sec. max.
After Glow		1 sec. max.
Char Length		1/2 in. max.